

Ctindo.

Walara Series 430W G3P

Australia's first manufactured n-type solar pv module.

Australian Made.

The Walara Series is a true evolution in Australian renewable energy industry manufacturing. Designed and engineered by a local team based in South Australia who are available for service and warranty support.

High Efficiency Cells.

The first Australian made panel featuring N-Type technology intergrated into premium power class laser-cut bifacial cells for higher output, higher efficiency and increased durability.

Intelligent Design.

Specially designed stronger, rigid 35_{mm} frame with less flex, protecting the cells and increasing integrity and longevity through less micro-cracks.

Zero Defect Manufacturing Process.

Our Zero-Defect Manufacturing process guarantees that every Tindo panel undergoes rigorous testing at 7 predetermined quality checkpoints ensuring high performance for the lifetime of the product.

Proven Performance in Australia's Harshest Conditions.

Our panels are mounted and performing everyday at the Desert Knowledge Testing Centre in Alice Springs. Tindo panels are consistently one of the highest performing panels at the centre. – dkasolarcentre.com.au











Walara 430G3P Data Sheet

Mechanical Characteristics		
Cells per panel	108 Half Cells	
Cell Type	N-Type Cells (182 x 182mm)	
Panel Dimension	1722 x 1133 x 35 mm	
Panel Weight	22 Kg	
Front Glass	3.2mm Fully tempered Double ARC Glass	
Frame	Anodized Aluminum Alloy (T6) / Black	
Junction Box	3 bypass diodes / IP68 rated	
Cable	1200 mm(+/-), 4mm2 or Customised Length	
Connector Type	Stabli-MC4 / KST4-EV0 2(M), KBT4-EVO 2(F)	

Thermal Characteristics				
RATING		UNIT	VALUE	
Operating Temperature		%	-40 ~ +85	
Maximum System Voltage (IEC)		VDC	1500	
Maximum Series Fuse Rating		Α	30	
Nominal Module Operating Temperature		°C	45 ± 2	
Temperature Coefficient	lsc	%/°C	0.045	
	Voc	%/°C	-0.25	
	Pmax	%/°C	-0.32	

Qualification test	
Thermal cycling test	- 40°C to 85°C for 200 cycles
Damp heat test	85°C and 85% relative humidity for 1000 hr
Mechanical Load test	5400Pa (Front) / 2400Pa (Rear)
PID test	1500 VDC, 96h, 85% RH, 85°C
Hail Impact test	25mm hail at 23m/s from 1m distance


Cyclone tested by Structural Engineering Consultants Australia (SECA) Pty Ltd certificate available on request

Safety factor of *static load test: 1.5 (Test load = Design load x Safety factor) # NexTracker installation : Front load 1800 Pa / Back Load 1800 Pa

Safety Ratings & Warranties		
Safety Application Class	Class II	
Fire Safety Classification	Class C	
Certifications	IEC 61215 , IEC 61730	
Warranty	25 years limited product warranty	
Performance Guarantee	25 years limited warranty 87.4% power	

Electrical characteristics			
108HC Cell Module Walara-			-430G3P
ITEM	UNIT	STC*	NMOT**
Max. Power (Pmax)	Wp	430	327.7
Max. Power voltage (Vmp)	V	32.38	30.53
Max. Power current (Imp)	А	13.28	10.73
Open circuit voltage (Voc)	V	39.09	37.15
Short circuit current (Isc)	А	14.08	11.35
Module efficiency	%	2	2.0
Positive power tolerance	W	0 ~	+ 5

- *STC (Standard Test Condition): 1,000 W/m2 , AM 1.5, 25°C
- **NMOT(Nominal Module Operating Temperature): Irradiance at 800W/m, Ambient Temperature 20°C, Wind Speed 1m/s, air mass of AM1.5
- # Tolerance of Measuring Pmax, Voc & Isc \pm 3% within each watt class at STC



Packaging		
Stacking Method	Horizontal	Vertical (Optional)
Panels per Pallet	30	31
Loading Capacity (40HQ)	600	806

- Note:
 The specifications included in this datasheet are subject to change without notice.
- The electrical data given here is for reference purpose only.

